Specifications

	Light Filtering	Blackout / Façade Blackout
Composition	100% Polyester	100% Polyester
Coating	Stiffened with Acrylic	Acrylic Foam Backing
Openness Factor	Light Filtering Approximately 1%	Blackout
Weight	6.93 oz/yd2 (235g/m2)	12.68 oz/yd2 (430g/m2)
Thickness	.019 in (.48mm)	0.022 in (.55mm)
Average length	27 yd/roll (25m)	22yd/roll (20m)
Width	118" (3m)	118" (3m)
Cutting	Knife, Crush, Ultrasonic	Knife, Crush, Ultrasonic
Welding	330-360°F. Test First	330-360°F. Test First
Railroadable	No	No
Cleaning	Wipe clean with warm soapy water and damp cloth.	Wipe clean with warm soapy water and damp cloth.
Fire Classifications	NFPA 701	NFPA 701, CAN/ULC-S109
Environmental Standards	GREENGUARD Gold, Low VOC <0.5mg/m3: CDPH Standard Method v1.1-2010, Health Product Declaration, OEKO-TEX Standard 100	

Features

















ENERGY SAVING





9001









Mesa Light Filtering and Blackout



Dove White

LF | BO



LF | BO

Pearl

ВО



LF | BO

ВО



Nougat

LF | BO

Dune

ВО







TEXSTYLE

Mesa Collection

A fabric collection designed to

seamlessly integrate with your

interior and exterior color scheme











ВО













ВО

Mesa Façade Blackout


ВО















ВО

Storm Façade

Black Façade

Tuxedo Façade





Certifications

OEKO-TEX®

CONFIDENCE IN TEXTILES

Tested for harmful substances. www.oeko-tex.com/standard100

GREENGUARD

A Division of Rollease Acmeda texstyle.com





